

ON Semiconductor

Is Now

onsemi™

To learn more about onsemi™, please visit our website at
www.onsemi.com

onsemi and **onsemi** and other names, marks, and brands are registered and/or common law trademarks of Semiconductor Components Industries, LLC dba "**onsemi**" or its affiliates and/or subsidiaries in the United States and/or other countries. **onsemi** owns the rights to a number of patents, trademarks, copyrights, trade secrets, and other intellectual property. A listing of **onsemi** product/patent coverage may be accessed at www.onsemi.com/site/pdf/Patent-Marking.pdf. **onsemi** reserves the right to make changes at any time to any products or information herein, without notice. The information herein is provided "as-is" and **onsemi** makes no warranty, representation or guarantee regarding the accuracy of the information, product features, availability, functionality, or suitability of its products for any particular purpose, nor does **onsemi** assume any liability arising out of the application or use of any product or circuit, and specifically disclaims any and all liability, including without limitation special, consequential or incidental damages. Buyer is responsible for its products and applications using **onsemi** products, including compliance with all laws, regulations and safety requirements or standards, regardless of any support or applications information provided by **onsemi**. "Typical" parameters which may be provided in **onsemi** data sheets and/or specifications can and do vary in different applications and actual performance may vary over time. All operating parameters, including "Typicals" must be validated for each customer application by customer's technical experts. **onsemi** does not convey any license under any of its intellectual property rights nor the rights of others. **onsemi** products are not designed, intended, or authorized for use as a critical component in life support systems or any FDA Class 3 medical devices or medical devices with a same or similar classification in a foreign jurisdiction or any devices intended for implantation in the human body. Should Buyer purchase or use **onsemi** products for any such unintended or unauthorized application, Buyer shall indemnify and hold **onsemi** and its officers, employees, subsidiaries, affiliates, and distributors harmless against all claims, costs, damages, and expenses, and reasonable attorney fees arising out of, directly or indirectly, any claim of personal injury or death associated with such unintended or unauthorized use, even if such claim alleges that **onsemi** was negligent regarding the design or manufacture of the part. **onsemi** is an Equal Opportunity/Affirmative Action Employer. This literature is subject to all applicable copyright laws and is not for resale in any manner. Other names and brands may be claimed as the property of others.

Board Level Application Notes for Sawn Singulated DFN and QFN Wettable Flank Packages



ON Semiconductor®

www.onsemi.com

INTRODUCTION

Various ON Semiconductor components are packaged in an advanced Dual or Quad Flat – Pack No – Lead package (DFN/QFN). The DFN/QFN platform represents the latest in surface mount packaging technology. It is important to follow the suggested board mounting guidelines outlined in this document. These guidelines include printed circuit board mounting pads, solder mask and stencil pattern and assembly process parameters.

QFN/DFN Packages

Current standard QFN/DFN packages are typically sawn or stamped to singulate the package from the strip during package assembly. This process will allow exposed copper surfaces from the side of the lead that is used for the substrate for this style of package. Fig 1, below illustrates a bottom view of QFN package with Sn-plated leads (and flag) with exposed Cu on the side of the leads. This is typical for standard QFN/DFN packages assembled today. This exposed copper on the side wall of the leads will not typically wet during solder reflow to PCB board mount. Fig 2 illustrates a side view of a DFN mounted to the PCB with non-wettable flank leads. No side wall wetting was observed.




Figure 1. Bottom View of 32 Pin QFN with Sn plating on bottom side and exposed Cu on side of leads

APPLICATION NOTE




Figure 2. Shows DFN package mounted to PCB with no side wall wetting to the leads

Figure 3 below shows a cross section of the DFN package mounted to PCB board with non-wettable side leads. Note, solder did not wet up the side of the leads after board mount reflow process.




Figure 3. Shows DFN Package cross-section thru center of two leads to show no wetting of the solder up the side of the leads

Wettable Flank QFN/DFN Packages

The industry has been slowly adopting a new version of the QFN/DFN style package that allows them to inspect solder joints from the side of the package. This allows customers to use standard AOI inspection equipment to determine if a unit is mounted to the PCB boards adequately without having to use x-ray inspection which could be more time consuming and more costly. These type of QFN/DFN packages with plating on the side of leads of the package are referred to as “Wettable Flank” QFN/DFN Packages.

Figure 4 shows a side view of a DFN package with wettable flanks mounted to the PCB board. Note, all leads exhibit solder wetting up the side of the leads.

Wettable Flank

Wettable flanks are optional for DFN/QFN packages. ON Semiconductor is offering 3 types of wettable flank options for sawn QFN/DFN packages. The option depends on the package type and assembly location.

Available Wettable Flank Sawn Options:





Figure 4. DFN Package with Wettable Flank Leads Showing Good Wetting and Fillet of Solder




Figure 5. Electro-less Plated Sn Wettable Flank with Cross Section View Mounted to PCB





Figure 6. Electro-plated Sn Step-cut Design with Cross Section View Mounted to PCB




Figure 7. Dimple Lead Design with Cross Section View Mounted to PCB

Printed Circuit Board Solder Pad Design Guidelines

The DFN/QFN board mounting process can be optimized by first defining and controlling the following:

1. PCB solder pad design.
2. PCB solder mask design.
3. Solderable metallization on PCB pads.
4. Solder screening onto PCB pads.
5. Choice of solder paste.
6. Package placement.
7. Reflow of the solder paste.
8. Final inspection of the solder joints.

Recommendations for each of these items are included in this application note.

Printed Circuit Board Solder Pad Design Guidelines

Refer to the case outline (specification sheet) drawing for the specific DFN/QFN package to be mounted. Based on the case outline’s “nominal” package footprint dimensions, the PCB mounting pads need to be larger than the nominal package footprint (See Figure 8).

NOTE: For wettable flank leads we suggest that the PCB pads be designed at least 0.45 mm longer than the nominal package footprint as shown in Figure 8. This will allow for an adequate fillet size that can be visibly inspected by AOI equipment.




Figure 8. 10 Pin DFN Package Footprint Shown with PCB Mounting Pads

PRINTED CIRCUIT BOARD SOLDER MASK DESIGN GUIDELINES

SMD and NSMD Pad Configurations

Two types of PCB solder mask opening commonly used for surface mount leadless style package are:

1. Non Solder Masked Defined (NSMD)
2. Solder Masked Defined (SMD)




Figure 9. Comparison of NSMD vs. SMD Pads

As their titles describe, the NSMD contact pads have the solder mask pulled away from the solderable metallization, while the SMD pads have the solder mask over the edge of the metallization, as shown in Figure 5. With the SMD Pads, the solder mask restricts the flow of solder paste on the top of the metallization which prevents the solder from flowing along the side of the metal pad. This is different from the NSMD configuration where the solder will flow around both the top and the sides of the metallization.

Typically, the NSMD pads are preferred over the SMD configuration since defining the location and size of the copper pad is easier to control than the solder mask. This is based on the fact that the copper etching process is capable of a tighter tolerance than the solder masking process. This also allows for visual inspection of solder fillet.

In addition, the SMD pads will inherently create a stress concentration point where the solder wets to the pad on top of the lead. This stress concentration point is reduced when the solder is allowed to flow down the sides of the leads in the NSMD configuration.

When dimensionally possible, the solder mask should be located within a range of 0.0762–0.1270 mm (0.003–0.005 in) away from the edge of the PCB mounting pad (See Figure 10). This spacing is used to compensate for the registration tolerances of the solder mask process, as well as to insure that the solder is not inhibited by the mask as it reflows along the sides of the metal pad.

The solder mask web (between openings) is the controlling factor in the pattern, and needs to be held to a minimum of 0.1016 mm (0.004 in). This minimum is the current PCB suppliers standard minimum web for manufacturability. Because of this web restriction, solder mask openings around PCB pads may need to be less than

the recommended shown. Whenever possible, keeping to the range given will provide for the best results.

Due to ever shrinking packages with finer pitches between mounting pads, a solder mask web may not be possible. It may be necessary to have a single solder mask window opening around the package without solder mask web between mounting pads. When this occurs, care must be taken to control the solder during reflow. Where the web aided in controlling the solder, in its absence, solder may bridge between mounting pads causing shorts.




Figure 10. Typical DFN Package – PCB Mounting Pads Shown with Solder Mask Openings (NSMD)

PCB Solderable Metallization

There are currently three common solderable coatings which are used for PCB surface mount devices – OSP, ENiAu and HASL. In any case, it is imperative that the coating is uniform, conforming, and free of impurities to insure a consistent solderable system.

The first coating consists of an Organic Solderability Protectant (OSP) applied over the bare copper feature. OSP coating assists in reducing oxidation in order to preserve the copper metallization for soldering. It allows for multiple passes through reflow ovens without degradation of the solderability. The OSP coating is dissolved by the flux when the solder paste is applied to the metal features. Coating thickness recommended by OSP manufacturers is between 0.25 and 0.35 microns.

The second coating is plated electroless nickel/immersion gold over the copper pad. The thickness of the electroless nickel layer is determined by the allowable internal material stresses and the temperature excursions the board will be subjected to throughout its lifetime. Even though the gold metallization is typically a self-limiting process, the thickness should be at least 0.05 microns thick, but not

consist of more than 5% of the overall solder volume. Excessive gold in the solder joint can create gold embrittlement. This may affect the reliability of the joint.


The third PCB pad protective coating option is Hot Air Solder Level (HASL); SnPb. Since the HASL process is not capable of producing solder joints with consistent height, this pad finish is not recommended for DFN/QFN type packages. Inconsistent solder deposition results in dome-shaped pads of varying height. As the industry moves to finer and finer pitch, solder bridging between mounting pads becomes a common problem with this coating.

Solder Screening onto the PCB

Stencil screening the solder paste onto the PCB is commonly used in the industry. The recommended stencil thickness used is 0.075 mm to 0.127 mm (0.003 in to 0.005 in). The sidewalls of the stencil openings should be tapered approximately 5° along with an electro-polish finish to aid in the release of the paste when the stencil is removed from the PCB.

On a typical 0.5 mm pitch or larger DFN/QFN the stencil opening for the perimeter pattern should be the same size as the PCB mounting pad. The center stencil opening for the center mounting pad(s) should allow for 70–80% coverage of the center mounting pad(s). (See Figure 11) Dividing the larger die pads into smaller screen openings reduces the risk of solder voiding and allows the solder joints for the smaller terminal pads to be at the same height as the larger ones.

On less than a 0.5 mm pitch DFN/QFN the stencil opening for the perimeter pattern should be the same size as the device nominal footprint. The center stencil opening for the center mounting pad(s) should allow for 60–70% coverage of the center mounting pad(s). (See Figure 12) Dividing the larger die pads into smaller screen openings reduces the risk of solder voiding and allows the solder joints for the smaller terminal pads to be at the same height as the larger ones.



Color Legend
 For Stencil Openings used in Figure 7 and 8.

- █ Package Outline
- █ PCB Center Mounting Pads
- █ Stencil Opening

Figure 11. Typical for 0.5 mm Pitch or Greater DFN/QFN Package with Stencil Opening Shown Over PCB Mounting Pads




Figure 12. Typical Less than 0.5 mm Pitch DFN/QFN Package with Stencil Opening Shown Over PCB Mounting Pads

Solder Paste

Solder paste such as Cookson Electronics’ WS3060 with a Type 3 or smaller sphere size is recommended. The WS3060 has a water – soluble flux for cleaning. Cookson Electronics’ PNC0106A can be used if a no – clean flux is preferred.

Package Placement onto the PCB

An automated pick and place procedure with magnification is recommended for component placement

Solder Reflow

Once the component is placed on the PCB, a standard surface mount reflow process can be used to mount the part. Figures 13 and 14 are examples of typical reflow profiles for lead free and standard eutectic tin lead solder alloys, respectively.

The preferred profile is provided by the solder paste manufacturer and is dictated by variations in chemistry and viscosity of the flux matrix in the solder paste. These variations may require small adjustments to the profile for process optimization.

In general, the temperature of the part should increase by less than 2°C/sec during the initial stages of reflow. The soak zone occurs at approximately 150°C and should last for 60 to 180 seconds for lead free profiles (30 – 120 sec for eutectic tin lead profiles). Typically, extending the length of time in the soak zone reduces the risk of voiding within the solder. The temperature is then increased. Time above the liquidus of the solder is limited to 60 to 150 seconds for lead free profiles (30 – 100 sec for eutectic tin lead profiles) depending on the mass of the board. The peak temperature of the profile should be between 245°C and 260°C for lead free solder alloys (205°C and 225°C for eutectic tin lead solders).

If required, removal of the residual solder flux can be done using the recommended procedures set forth by the flux manufacturer.

since the pads are on the underside of these packages. A dual image optical system enables alignment of the underside of the package to the PCB and should be used. Pick and place equipment with the standard tolerance of ±0.05 mm (0.002 in) or better is recommended. Once placed onto the board, the package self – aligns during the reflow process due to surface tension of the solder.




Figure 14. Typical Reflow Profile for Eutectic Tin / Lead Solder

Final Solder Inspection

Solder joint integrity is determined by using an X-ray inspection system. With this tool, defects such as shorts between pads, open contacts, and voids within the solder and extraneous solder can be identified. In addition, the mounted device should be rotated on its side to inspect the side of the solder joints for acceptable solder joint shape and stand-off height. The solder joints should have enough solder volume and stand – off height so that an “Hour Glass” shaped connection is not formed as shown in Figure 11. “Hour Glass” solder joints are a reliability concern and should be avoided.




Figure 13. Typical Reflow Profile for Lead Free Solder




Figure 15. Illustration of Preferred and Undesirable Solder Joints11.

Rework Procedure

Since the DFN/QFN's are leadless devices, the package must be removed from the PCB if there is an issue with the solder joints.

Standard SMT rework systems are recommended for this procedure since airflow and temperature gradients can be carefully controlled. It is also recommended that the PCB be placed in an oven at 125_C for 4 to 8 hours prior to package removal to remove excess moisture from the packages. In order to control the region which will be exposed to reflow temperatures, the PCB should be heated to 100_C by conduction through the backside of the board in the location of the device. Typically, heating nozzles are then used to increase the temperature locally and minimize any chance of overheating neighboring devices in close proximity.

Once the device's solder joints are heated above their liquidus temperature, the package is quickly removed and the pads on the PCB are cleaned. The cleaning of the pads is typically performed with a blade*style conductive tool with a de*soldering braid. A no clean flux is used during this process in order to simplify the procedure.


Solder paste is then deposited or screened onto the site in preparation of mounting a new device. Due to the close

proximity of the neighboring packages in most PCB configurations, a miniature stencil for the individual component is typically required. The same stencil design that was originally used to mount the package can be applied to this new stencil for redressing the pads.

Due to the small pad configurations of the DFN/QFN, and since the pads are on the underside of the package, a manual pick and place procedure with the aid of magnification is recommended. A system with the same capabilities as described in the **Package Placement** section should be used.

Remounting the component onto the PCB can be accomplished by either passing it through the original reflow profile, or by selectively heating the specific region on the PCB using the same process used to remove the defective package. The benefit of subjecting the entire PCB to a second reflow is that the new part will be mounted consistently using a previously defined profile.

The disadvantage is that all of the other soldered device will be reflowed a second time. If subjecting all of the parts to a second reflow is either a concern or unacceptable for a specific application, then the localized reflow option is the recommended procedure. Optimal board mounting results can be achieved by following these suggested guidelines.

ON Semiconductor and  are trademarks of Semiconductor Components Industries, LLC dba ON Semiconductor or its subsidiaries in the United States and/or other countries. ON Semiconductor owns the rights to a number of patents, trademarks, copyrights, trade secrets, and other intellectual property. A listing of ON Semiconductor's product/patent coverage may be accessed at www.onsemi.com/site/pdf/Patent-Marking.pdf. ON Semiconductor reserves the right to make changes without further notice to any products herein. ON Semiconductor makes no warranty, representation or guarantee regarding the suitability of its products for any particular purpose, nor does ON Semiconductor assume any liability arising out of the application or use of any product or circuit, and specifically disclaims any and all liability, including without limitation special, consequential or incidental damages. Buyer is responsible for its products and applications using ON Semiconductor products, including compliance with all laws, regulations and safety requirements or standards, regardless of any support or applications information provided by ON Semiconductor. "Typical" parameters which may be provided in ON Semiconductor data sheets and/or specifications can and do vary in different applications and actual performance may vary over time. All operating parameters, including "Typicals" must be validated for each customer application by customer's technical experts. ON Semiconductor does not convey any license under its patent rights nor the rights of others. ON Semiconductor products are not designed, intended, or authorized for use as a critical component in life support systems or any FDA Class 3 medical devices or medical devices with a same or similar classification in a foreign jurisdiction or any devices intended for implantation in the human body. Should Buyer purchase or use ON Semiconductor products for any such unintended or unauthorized application, Buyer shall indemnify and hold ON Semiconductor and its officers, employees, subsidiaries, affiliates, and distributors harmless against all claims, costs, damages, and expenses, and reasonable attorney fees arising out of, directly or indirectly, any claim of personal injury or death associated with such unintended or unauthorized use, even if such claim alleges that ON Semiconductor was negligent regarding the design or manufacture of the part. ON Semiconductor is an Equal Opportunity/Affirmative Action Employer. This literature is subject to all applicable copyright laws and is not for resale in any manner.

PUBLICATION ORDERING INFORMATION

LITERATURE FULFILLMENT:

Literature Distribution Center for ON Semiconductor
19521 E. 32nd Pkwy, Aurora, Colorado 80011 USA
Phone: 303-675-2175 or 800-344-3860 Toll Free USA/Canada
Fax: 303-675-2176 or 800-344-3867 Toll Free USA/Canada
Email: orderlit@onsemi.com

N. American Technical Support: 800-282-9855 Toll Free
USA/Canada
Europe, Middle East and Africa Technical Support:
Phone: 421 33 790 2910

ON Semiconductor Website: www.onsemi.com

Order Literature: <http://www.onsemi.com/orderlit>

For additional information, please contact your local Sales Representative